

# TECHNİCAL DATA SHEET

## SAC305 NCL30 Solder Wire

Lead Free, No Clean, Halide Free



### **Description**

NCL30 Flux provided the fluxing activity levels that promote fast wetting and leaves clear residue with help of the NCL30 flux type. Halide free eliminates any long term corrosion potential.

For a high quality soldering, the purity of solder alloy and the correct flux with clear residue are the essential parts. Besides these properties, the working temperatures and the ultimate strength of the soldered joint are also important in soldering process.

NCL30 can be used for diffucult soldering applications like rework, repair and manuel-automatic soldering.

**SAC305** Solder alloy with NCL30 flux type classified according to J-STD-004B and EN 61190-1-3 as **RELO**. Also this product suitable for the **RoHS II**.

#### NCL30's advantages:

- Excellent wettability
- Fast soldering
- High spread speed
- Clear residues
- High reliability
- Noncorrosive

# **Technical Data & Phycical Properties**

Properties (J-STD-006B)	NCL 30 Flux		
Acid Value IPC-TM-650, 2.3.13	195-200 mg KOH / g ± %5		
Corrosion Test IPC-TM-650, 2.6.15	Passed		
Copper Mirror Test IPC-TM-650, 2.3.32	L		
Surface insulation resistance IPC-TM-650, 2.6.3.3	>1x10 E8 Ohm		
Bromide and chloride Test IPC-TM-650, 2.3.35	Not detected		
Silver Chromate Test IPC-TM-650, 2.3.33	Not Passed		
Solid Content, flux IPC-TM-650, 2.3.34	Not detected		
Fluoride after spot Test IPC-TM-650, 2.3.35.1	Passed		





# TECHNİCAL DATA SHEET

# SAC305 NCL30 Solder Wire

Lead Free, No Clean, Halide Free



Solder Composition:	Sn %96,5 (±0,15)
	Ag %3 (±0,15)
	Cu %0,5 (±0,15)
Melting Point:	217 °C Solidus
	220 °C Liquidus
Density:	7,34 g/cm <sup>3</sup>
Flux Content:	%1,1 - %2,2 - % 3
Avaible diameters:	from 0,4 mm

## **Packaging & Reels**

Kurtel Lead Free Solder Wire is available in nominal weights 500 gr reels in 10 kg packages.

### (500 gr) Reels dimensions:

<u>Dimensions</u>	500gr Reel	
Height	55 mm	
Outside dia.	55 mm	
İnside dia.	16 mm	

## **Storage & Shelf Life**

Kurtel SAC305 Solder Wires should be stored in dry at room temperature. Solder wire has an indefinite shelf life.

# **Health & Safety**

Before using please read the MSDS. Avoid contact directly by hand.





